

HORIZONTAL ROAD MARKINGS FOR ASPHALT

EXCELLENT ABRASION RESISTANCE

OUTDOOR RESISTANCE

EXTREME FAST DRYING

TRAFFICOAT

Series 0018

1K, UHS, fast drying, synthetic road marking paint



◆ General information

System: One pack - 1K

Nature: Solvent-based

Packages: 25 kg/L

Colors ready in stock: White



◆ Technical features

1K Ultra High Solid fast drying synthetic enamel for road marking. Road marking paint with good weather resistance, good elasticity and excellent abrasion resistance. The product is ideal for applications on asphalt when quick post-application walkability and resistance to the passage of vehicles are required. The product is ideal for applications on asphalt when quick post-application walkability and resistance to the passage of vehicles are required.

◆ Application field

Road marking paint suitable for horizontal road markings on asphalted, cemented and paved roads with leucitite-sampietrini. The paint is ideal for new works or for the review of horizontal road marking.

◆ Technical data

Theoretical average spreading rate	<i>4,3 m²/kg each coat at the dry film thickness of 70 μ</i>
---	---

Application	<i>Spray</i>
--------------------	--------------

Dilution	<i>20-25% with Anti-blooming Nitro Thinner Series D0002</i>
-----------------	---

Gloss	-
--------------	---

Wet film thickness each coat	<i>102 μ</i>
-------------------------------------	--------------

Dry film thickness each coat	<i>70 μ</i>
-------------------------------------	-------------

N° of coats	-
--------------------	---

Total dry film thickness	<i>90 μ</i>
---------------------------------	-------------

◆ Drying

Overcoating interval	-
-----------------------------	---

Air drying	<i>20°C - 25°C</i>
-------------------	--------------------

Dust-free drying	-
-------------------------	---

Dry to touch	<i>30 minutes</i>
---------------------	-------------------

Dry through	-
--------------------	---

Full cure	<i>7 days</i>
------------------	---------------

Flash off	-
------------------	---

Stoving drying	-
-----------------------	---