

ANTI-SLIP EFFECT CERTIFIED PRODUCT

Estalia Group proposes the product **PAVIDAM Serie 0252**, which, when combined with **5% Antiskid Additive Series 0851**, offers an anti-slip effect in accordance with **DM 236/1989**.

Ministerial Decree No. 236/1989 defines the technical requirements necessary to guarantee accessibility, adaptability, and visibility of private and publicly subsidised public residential buildings, for the purpose of overcoming and eliminating architectural barriers; in particular, Article 8.2.2 deals with the subject of anti-slip flooring, which, to be defined as such, must be made of materials whose coefficient of friction meets certain requirements.

The coefficient of friction is measured by means of the **B.C.R.A.** (British Ceramic Research Association Ltd.) method, where it is defined that it must have a value greater than 0.40 both in the case of a leather slipping element on dry surface and in the case of a standard hard rubber slipping element on wet surface.

The **B.C.R.A. method** is applied using an instrument that measures the dynamic coefficient of friction between a sliding element, slid by a small vehicle travelling at a constant speed, and the pavement, which is effectively the test surface.

The **Coefficient of Friction (COF) μ** values are divided into:

- **Dangerous slippery:** $\mu < 0.2$
- **Excessive slippery:** $0.2 \leq \mu < 0.4$
- **Satisfactory friction:** $0.4 \leq \mu < 0.74$
- **Excellent friction:** $\mu > 0.74$


PAVIDAM Serie 0252, when combined with **Antiskid Additive Series 0851**, is a product with an anti-skid effect as it achieved results in accordance with **Decree No. 236/1989**, shown in the table here below:

DRY TEST SURFACE (D), LEATHER SLIDING ELEMENT	
TYPE OF PATH:	COEFFICIENT OF FRICTION (COFd) μ
Straight	0.63
Diagonal to the right	0.63
Diagonal to the left	0.63
WET TEST SURFACE (water + detergent) (w), STANDARD HARD RUBBER SLIDING ELEMENT 4S	
TYPE OF PATH:	COEFFICIENT OF FRICTION (COFd) μ
Straight	0.72
Diagonal to the right	0.72
Diagonal to the left	0.74

The product is suitable for indoor use and can also be applied on cement floors and concrete substrates, thus showing dustproof and wearproof properties.

Castenedolo, 05/12/2024

TECHNICAL DIRECTOR

Stefano Tonini


ESTALIA Performance Coatings SpA

Sede legale/Amministrativa Via Giacomo Matteotti 160 - 25014 - Castenedolo - Brescia - Italy

Sede Operativa Via San Rocco, 10/1/A, 42027, Montecchio Emilia (RE) **Contatti:** Tel. +39 0522 11709- Fax +39 0522 865796

Partita IVA/C.F. IT03432100174 del 1/12/1997 · *R.E.A. n.* BS - 396070 · *Capitale Sociale* € 6.000.000

Contatti Tel. +39 030 21 35 55 - Fax +39 030 27 31 664 · *Web* www.color-damiani.com - www.estaliacoatings.com

Soggetta a direzione e coordinamento da parte di CIBINO S.r.l. C.F. 01746420981 ai sensi dell'articolo 2497-bis del C.C.